

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

**0 295 730
A1**

EUROPEAN PATENT APPLICATION

(12)

(21) Application number: 88200959.0

(22) Date of filing: 13.05.88

(51) Int. Cl.⁴ C08K 3/30 , C08L 69/00 ,
C08L 67/02

(30) Priority: 12.06.87 NL 8701369

(43) Date of publication of application:
21.12.88 Bulletin 88/51

(84) Designated Contracting States:
DE FR GB IT NL

(71) Applicant: GENERAL ELECTRIC COMPANY
1 River Road
Schenectady New York 12151(US)

(72) Inventor: Verhoeven, Jeroen Johannes
General Electric Plastics B.V. P.O. Box 117
NL-4600 AC Bergen op Zoom(NL)
Inventor: Roovers, Wilhelmus Marinus Maria
General Electric Plastics B.V. P.O. Box 117
NL-4600 AC Bergen op Zoom(NL)

(74) Representative: Schüler, Horst, Dr. et al
General Electric Praunheimer Landstrasse
50
D-6000 Frankfurt 90(DE)

(54) Polymer mixture comprising an aromatic polycarbonate and an aromatic polyester.

(57) The invention relates to polymer mixtures which comprise an aromatic polycarbonate and an aromatic polyester. The polymer mixtures are stabilised by the addition of a sulphurous compound.

Best Available Copy

EP 0 295 730 A1

Polymer mixture comprising an aromatic polycarbonate and an aromatic polyester.

The invention relates to a polymer mixture which comprises the following constituents:

- A. 1-98.99%, by preference 6-93.99%, by weight of an aromatic polycarbonate,
- B. 98.99-1%, by preference 6-93.99%, by weight of an aromatic polyester, and
- C. 0.01-5% by weight of a stabiliser.

5 it is known, for example, from GB-A-1466154 that polymer mixtures which comprise an aromatic polycarbonate and an aromatic polyester show a certain instability. Probably, a transesterification reaction occurs in such mixtures.

It is proposed in GB-A-1466154 to suppress said transesterification by the addition of a phosphorus-containing compound, for example, triphenyl phosphite, phosphorous acid.

10 The invention is based on the discovery that a further improvement of the stability can be obtained. The use of inorganic sulphurous stabilisers results in a slightly improved stability as compared with the known phosphorus-containing stabilisers.

The known phosphorus-containing stabilisers have the additional disadvantage that they show only a small stabilising activity in polymer mixtures which moreover comprise one or more pigments, for example, 15 ultramarine blue and titanium dioxide. It has quite unexpectedly been found that the stabilisers according to the invention also have a good activity in the presence of pigments.

JP-A-60-215050 describes polymer blends comprising 30-98.985% by weight of polyethylene terephthalate, 1-60% by weight glass fibres, a thioetherester of a specific formula and 0.005-5% by weight of a polycarbonate. The addition of the glass fibres, the thioetherester and the polycarbonate are claimed to 20 reduce the sink marks and to improve the appearance of polyethylene based compositions. This is not related with the prevention of transesterification of aromatic polycarbonate / aromatic polyester blends as claimed in this application. Applicant further found that similar thioetheresters do not prevent transesterification.

WO-87/00542 describes the addition of a metal salt of an aromatic sulfimide together with a metal 25 sulfate or bisulfate to carbonate polymers. Such addition is claimed to prevent reduction in molecular weight of the carbonate polymer during melt shearing. This is a phenomenon not related with transesterification.

The polymer mixture according to the invention may comprise 0.01-5% by weight, preferably 0.05-0.5% by weight, of a metal sulphate as a stabiliser. A suitable metal sulphate is zinc sulphate. Compared with the 30 known phosphorus-containing stabilisers, the said sulphate has the advantage of being recorded on the list of compounds approved of by FDA for contact with foodstuffs.

It is possible to use sulphuric acid or sulphurous acid as a stabiliser in the polymer mixtures according to the invention, preferably in a quantity from 0.01 to 1% by weight. This quantity by weight applies to a solution of 45% by volume. In the case of higher or lower concentrations the quantity by weight should be adapted accordingly.

35 As a stabiliser may further be used, for example, metal sulphites, metal bisulphites, metal hydrogen sulphates or metal thiosulphates.

The invention also relates to articles formed from the polymer mixtures according to the invention.

So the polymer mixture according to the invention comprises at any rate the following constituents in the above-indicated quantities:


- 40 A. aromatic polycarbonate,
- B. aromatic polyester,
- C. an inorganic sulphurous compound as a stabiliser.

The polymer mixture according to the invention may moreover comprise one or more of the following constituents:

- 45 D. one or more pigments
- E. conventional additives.

A. Aromatic polycarbonate

50 Aromatic polycarbonates are materials known per se. They are generally prepared by reacting a dihydric phenol compound with a carbonate precursor, for example, phosgene, a halogen formate or a carbonate ester. Aromatic polycarbonates are polymers which comprise units of the formula



wherein A is a bivalent aromatic radical derived from the dihydric phenol used in the preparation of the polymer. Mononuclear or polynuclear aromatic compounds which comprise two hydroxy radicals which are each directly bonded to a carbon atom of an aromatic nucleus may be used as dihydric phenols in the preparation of the aromatic polycarbonates.

10

The dihydric phenols are: 2,2-bis-(4-hydroxyphenyl)propane; hydroquinone; resorcinol; bis-(4-hydroxyphenyl)methane; bis-(4-

Examples of suitable dihydroxy phenols are: 2,2-bis-(4-hydroxyphenyl)propane; hydroquinone; resorcinol; 2,2-bis-(4-hydroxyphenyl)pentane; 2,4'-(dihydroxydiphenyl)methane; bis(2-hydroxyphenyl)methane; bis-(4-hydroxyphenyl)methane; bis-(4-hydroxy-5-nitrophenyl)methane; 1,1-bis-(4-hydroxyphenyl)ethane; 3,3-bis-(4-hydroxyphenyl)pentane; 2,2-dihydroxy-phenyl; 2,6-dihydroxynaphthalene; bis-(4-hydroxydiphenyl)sulphone; bis-(3,5-diethyl-4-hydroxyphenyl)sulphone; 2,2-bis-(3,5-dimethyl-4-hydroxyphenyl)propane; 2,4'-dihydroxyphenyl sulphone; 5'-chloro-2,4'-dihydroxydiphenyl sulphone; bis-(4-hydroxyphenyl) diphenyl sulphone; 4,4'-dihydroxydiphenyl ether; 4,4'-dihydroxy-3,3'-dichlorodiphenyl ether; 4,4'-dihydroxy-2,5-dihydroxydiphenyl ether.

Other dihydric phenols which are also suitable are described in US-A-2,999,835; 3,038,385; 3,334,154, and 4,131,575.

Other dihydric phenols which are also suitable are 4,131,575.

The aromatic polycarbonates can be prepared according to methods known per se: for example, by reacting a dihydric phenol with a carbonate precursor, for example, phosgene. For this purpose, reference may be made to the just-mentioned United States Patent Specifications and to US-A 4,018,750 and 4,123,426. They may also be prepared by a transesterification as described in US-A-3,153,008.

25 branched polycarbonates as described for example, in US-A-4,001,184 are also suitable.

26 branched polycarbonates which are obtained by

The known branched polycarbonates as described for example, in US-A-4,001,184 are also obtained by suitable aromatic polycarbonates are also the so-called polyester carbonates which are obtained by carrying out the polymerisation reaction in the presence of an ester precursor, for example, a difunctional ester-forming derivative thereof. These polyester carbonates have ester compounds and carbonate compounds in the polymeric chain. Polyester carbonates are described, for example, in US-A-3,169,121.

In the polymer mixtures according to the invention it is also possible to use as hardener a mixture of various polycarbonates as mentioned hereinbefore.

36 B. Aromatic polyester

B. Aromatic polyester

Any known aromatic polyester may be used in the polymer mixtures according to the invention. Polyesters which are particularly suitable are the polyalkylene terephthalates. Terephthalates are compounds known per se. They may be described as glycol esters of terephthalic acid. They are esters of terephthalic acid with a

Any known aromatic polyester may be used in the present invention. Polyesters which are particularly suitable are the polyalkylene terephthalates. Polyalkylene terephthalates are compounds known per se. They may be described as glycol esters of terephthalic acid. They may be prepared, for example, by alcoholysis of esters of terephthalic acid with a glycol succeeded by a polymerisation reaction, by heating glycol compounds with free acids or derivatives thereof. The glycol part of the polyalkylene terephthalates may comprise from 2 to 10 carbon atoms; it preferably comprises from 2 to 4 carbon atoms in the form of linear alkylene chains. The glycol compounds preferably used which are derived from ethylene glycol or butane-1,4-diol and terephthalic acid, or from ethylene glycol and isophthalic acid, or from the said glycol and/or of the terephthalic acid and/or of the isophthalic acid, are known per se.

45 Polyester are preferably used which are derived from ethylene glycol or butane-1,4-diol and terephthalic acid. It is also possible to use copolyesters in which a part of the said glycol and/or of the terephthalic acid is replaced by another glycol and/or aromatic carboxylic acid. In general, not more than 30 mol.%, preferably not more than 10 mol.%, of the glycol and/or terephthalic acid is replaced by other comonomers in such copolyesters.

It is also possible to use so-called block copolyesters as a polyalkylene terephthalate. These block copolyesters are prepared, for example, by converting a polybutylen terephthalate with reactive terminal groups with a reactive polyester or copolyester in the presence of a transesterification catalyst.

It is further possible to incorporate a branching agent in the polyalkylene terephthalate. The branching agent may be a glycol having three or more hydroxyl groups or a trifunctional or polycarboxylic acid. It is also possible to use a mixture of various polyesters as the polyester.

It is also possible to use a mixture of various polyesters as the polyester.

C. Sulphurous compound as a stabiliser

The polymer mixture according to the invention comprises an inorganic sulphurous compound as a stabiliser. Suitable sulphurous compounds are, for example, metal sulphates, for example, zinc sulphate, sulphuric acid, sulphurous acid, metal sulphites, metal bisulphites, metal hydrogen sulphate and metal thiosulphates. The stabiliser may be used in a quantity from 0.01-5% by weight. Metal sulphates are preferably used in a quantity from 0.05-0.5% by weight of sulphuric acid and sulphurous acid in a quantity of preferably 0.01-1% by weight.

In addition to the constituents mentioned hereinbefore sub A, B and C, the polymer mixtures according to the invention may comprise one or more of the following constituents:

D. Pigments

The stabilisers as used in the polymer mixtures according to the invention have the advantage that they do not lose, or that they hardly lose, their effect in the presence of pigments.

Therefore, the polymer mixtures according to the invention may comprise one or more pigments, for example, ultramarine blue and titanium dioxide.

E. Conventional additives

The polymer mixture according to the invention may comprise as additives, for example, polyolefins, mould-release agents, agents to improve the flame-retarding properties, further stabilisers, for example, thermal stabilisers, dyes, fillers and reinforcing fillers, for example, glass fibres.

More in particular, the polymer mixture according to the invention may also comprise a combination of several of the various additives mentioned hereinbefore.

The polymer mixture according to the invention preferably comprises a weight ratio of the quantity of polycarbonate (A) to aromatic polyester (B) between 1:8 and 8:1.

The polymer mixture according to the invention may be prepared according to conventional methods of preparing polymer mixtures, for example, by melt extrusion.

The invention will now be described in greater detail with reference to the ensuing specific examples:

Comparative examples A, B, C and D, examples I, II, III and IV.

Eight polymer mixtures were prepared having a composition as recorded in Table I hereinafter. The constituents used were as follows:

PBT : Polybutyleneterephthalate having an intrinsic viscosity of 1.18 dl/g measured in a 60/40 mixture of phenol and 1,1,2,2-tetrachloroethane at 25°C.

PC : Polycarbonate derived from bisphenol A and phosgene having an intrinsic viscosity of 53.0 ml/g measured in methylene chloride (CH_2Cl_2) at 25°C.

FOS : Phosphite, namely a mixture of various aromatic and aliphatic phosphites.

SULF : Zinc sulphate

H_2SO_3 : sulphurous acid (45% by vol. in water)

H_2SO_4 : Sulphuric acid (45% by volume in water)

Pigment : Ultramarine blue: pigment blue 29

TiO_2 : Titanium dioxide.

The indicated constituents were extruded together on a double-blade extruder at a melting temperature of approximately 285°C and a speed of 200 rpm.

The stability against transesterification was determined as follows. Test pieces for determining the Vicat-B value according to DIN 53460 were injection-moulded from the polymer mixtures according to Examples I, II, III and IV and according to comparative examples A, B, C and D. The test pieces were injection-moulded under extra heavy conditions (285°C, residence time 8 minutes). In a transesterification reaction, products are formed with a lower Vicat value as compared to the Vicat value of the polycarbonate resin. This results in an overall reduction of the Vicat value of the blend.

So a lower Vicat value indicates a transesterification: the higher the Vicat, the stabler the polymer

mixture.

The resulting test pieces were also evaluated visually with regard to surface defects (so-called "splay"). Such surface defects often occur as a result of transesterification reactions.

The results found are recorded in Table I:

Table I

Example A B C D I II III IV

Composition
(parts by weight)

		45	43	45	43	45	45	45	43
15	o PBT	45	43	45	43	45	45	45	43
	o PC	55	53	55	55	55	55	55	55
	o Fos	-	-	0.2	0.2	-	-	-	0.2
	o Sulf	-	-	-	-	0.4	-	-	-
20	o H ₂ SO ₃	-	-	-	-	-	0.09	-	-
	o H ₂ SO ₄	-	-	-	-	-	-	0.11	-
	o Pigment	-	-	3.5	-	3.5	-	-	3.5
25	o TiO ₂	-	0.5	-	0.5	-	-	-	0.5

Properties

30	o Vicat B 80	80	124	97	127	120	120	126
	(°C)							

o Splay* + + - + - - - -

* - no or slight "splay"; + strong splay

It may be seen from the results of Table I that the polymer mixtures according to the invention (examples I, II, III and IV) generally have the same to a slightly better stability than the comparative polymer mixtures A, B, C and D.

It strikes in particular that the polymer mixture according to example D has a much worse stability than the corresponding example IV according to the invention. The known phosphite stabiliser obviously loses its activity in the presence of pigments. The stabiliser according to the invention does not exhibit said disadvantage.

Claims

1. A polymer mixture which comprises the following constituents:
 - A. 1-99.99% by weight of an aromatic polycarbonate,
 - B. 99.99-1% by weight of an aromatic polyester, and
 - C. 0.01-5% by weight of a stabiliser,
 characterised in that the polymer mixture comprises an inorganic sulphurous compound as the stabiliser.

2. A polymer mixture as claimed in claim 1, wherein the mixture comprises
 - A. 6-93.99% by weight of an aromatic polycarbonate,
 - B. 6-93.99% by weight of an aromatic polyester, and
 - C. 0.01-5% by weight of a stabiliser,
- 5 characterised in that the polymer mixture comprises an inorganic sulphurous compound as the stabiliser.
3. A polymer mixture as claimed in Claim 1, characterised in that the polymer mixture comprises in addition a pigment.
4. A polymer mixture as claimed in Claim 2, characterised in that the polymer mixture comprises ultramarine blue as a pigment.
- 10 5. A polymer mixture as claimed in Claim 1, characterised in that the polymer mixture comprises in addition one or more conventional additives.
6. A polymer mixture as claimed in Claim 1, characterised in that the polymer mixture comprises as a stabiliser 0.01-5% by weight, preferably 0.05-0.5% by weight, of a metal sulphate, preferably zinc sulphate.
7. A polymer mixture as claimed in Claim 1, characterised in that the polymer mixture comprises 0.01-15 1% by weight of sulphuric acid or sulphurous acid as a stabiliser.
8. A polymer mixture as claimed in Claim 1, characterised in that the polymer mixture comprises as a stabiliser 0.01-5% by weight of a metal sulphite, a metal bisulphite, of a metal hydrogen sulphate or of a metal thio sulphate.
9. Articles formed from the polymer mixture as claimed in Claim 1.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 88 20 0959

DOCUMENTS CONSIDERED TO BE RELEVANT			Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
Category	Citation of document with indication, where appropriate, of relevant passages			
X	PATENT ABSTRACTS OF JAPAN, vol. 10, no. 78 (C-335)[2135], 27th March 1986, page 85 C 335; & JP-A-60 215 050 (MITSUBISHI RAYON K.K.) 28-10-1985 * Abstract *	1	C 08 K 3/30 C 08 L 69/00 C 08 L 67/02	
A	US-A-4 576 982 (TYRELL et al.) * Claims 1-26 *	1-8		
A	US-A-4 510 196 (CARTER Jr.) * Claims 1-14 *	1-8		
A	DE-A-2 631 755 (GENERAL ELECTRIC) * Claims 1-10 *	1-8		
A	FR-A-2 154 783 (BAYER) * Claims 1-6; table I *	1-8		
A	WO-A-8 700 542 (DOW CHEMICAL) * Claims 1-9 *	1-8		
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)	
			C 08 K C 08 L	
The present search report has been drawn up for all claims			Examiner	
Place of search	Date of completion of the search	DECOCKER L.		
THE HAGUE	26-09-1988			
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons a : member of the same patent family, corresponding document		
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document				

EPO FORM 1503 (01/82) (FPO/01)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.